



CORROSION EXPOSURE CHART

DEFINITION OF RATINGS

- **EXCELLENT**
No effect on normal coating life
- **GOOD**
Minimal effect on coating life
- **FAIR**
Useable, but reduced coating life
- **NOT RECOMMENDED**
Impractical coating life

- Splash & Spill/Short Intervals
- Direct Exposure/Extended Intervals

		WATER		ORGANIC ACIDS							INORGANIC ACIDS							ALKALIS																							
		Fresh Salt	Fresh, 65.6 °C Salt, 65.6 °C	Acetic 10%	Acetic, Glacial	Benzoic	Citric 10%	Lactic, Dilute	Maleic 25%	Oleic 100%	Picric 10%	Fatty Acids 100%	Boric	Hydrochloric (Concen.) 37%	Hydrochloric 20%	Hydrochloric 10%	Hydrofluoric 40%	Nitric 30%	Nitric 10%	Phosphoric 85%	Phosphoric 50%	Phosphoric 20%	Sulphuric 98%	Sulphuric 10-50%	Sulfuric 10%	Ammonium Hydroxide 28%	Ammonium Hydroxide 10-20%	Calcium Hydroxide, Dilute	Potassium Hydroxide (Sat'd)	Potassium Hydroxide 50%	Potassium Hydroxide 25%	Sodium Hydroxide 10%	Sodium Hydroxide 70%	Sodium Hydroxide 50%	Sodium Hydroxide 25%	Sodium Hydroxide 10%					
Alkyd Urethanes & Enamels	V200 Alkyd Urethane Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○		
	V201 Alkyd Urethane Semi-Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○		
	V210 Water Reducible Alkyd Enamel	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V220 Rapid Dry Alkyd Enamel	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V225 High Solids Rapid Dry Enamel	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V230 Quick Dry Alkyd Enamel Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V231 Quick Dry Alkyd Enamel Semi-Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V260 Electrostatic Enamel Semi-Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
WB Acrylics	V300 Quick Dry Acrylic Spray DTM Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V330 Acrylic DTM Enamel Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V331 Acrylic DTM Enamel Semi-Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
	V341 PreCatalyzed Waterborne Epoxy Semi-Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
	V342 PreCatalyzed Waterborne Epoxy Eggshell	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
2-Component Epoxies	V157 Coal Tar Epoxy	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V160 Epoxy Mastic Coating	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
	V400 Polyamide Epoxy Coating	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
	V410 Fast Dry Polyamide Epoxy	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
	V430 100% Solids Epoxy	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
	V440 Amine Adduct Epoxy	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
	V450 Acrylic Epoxy	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
2-Component Urethanes	V500 Aliphatic Acrylic Urethane Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V510 Aliphatic Acrylic Urethane Semi-Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
	V515 Aliphatic Urethane Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
	V520 Polyester Urethane Gloss	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○

NOTE: all coatings must be fully cured to meet these exposures
NOTE: this chart covers finish coats only, use primers recommended on individual finish coat technical data sheet
NOTE: proper surface preparation is critical to obtain resistance in all cases

Benjamin Moore & Co., Limited makes no guarantee as to the suitability of any product listed on this chart in the presence of any chemical reagent. All tests for resistance were completed under laboratory conditions. Temperature, humidity and other factors influence the rate at which certain chemicals react with coatings. For best results, test each coating in actual field conditions for suitability.

Fading and chalking may occur on certain product types, however chemical resistance is generally not compromised.

CORROSION EXPOSURE CHART

COROTECH
HIGH PERFORMANCE

DEFINITION OF RATINGS

- **EXCELLENT**
No effect on normal coating life
- **GOOD**
Minimal effect on coating life
- **FAIR**
Useable, but reduced coating life
- **NOT RECOMMENDED**
Impractical coating life

- Splash & Spill/Short Intervals
- Direct Exposure/Extended Intervals

		GASES				SOLVENTS						FATS/OILS	ACID SALTS			ALKALINE SALTS			MISC.		WEATHER																							
		Chlorine, Dry	Chlorine, Wet	Sulphur Dioxide, Dry	Sulphur Dioxide, Wet	Hydrogen Sulfide, Wet	Acetone	Alcohol	Benzene	Carbon Tetrachloride	Chloroform	Ethylene Chloride	Gasoline	Ketones	Toluene	Trichloroethylene	Xylene	Dry Cleaning, Solvents	Animal	Vegetable	Mineral	Aluminum Nitrate 10%	Ammonium Chloride	Copper Sulfate	Ferric Nitrate	Zinc Sulfate	Barium Sulfide	Sodium Sulfide	Sodium Bicarbonate	Sodium Carbonate	Sodium Sulfide	Trisodium Phosphate 10%	Formaldehyde 37%	Phenol 5%	Refinery Crudes	Hydraulic Fluids	Transmission Fluids	Skydrol	Coastal	Inland Industrial	Inland Commercial			
Alkyd Urethanes & Enamels	V200 Alkyd Urethane Gloss	●																																										
	V201 Alkyd Urethane Semi-Gloss	○																																										
	V210 Water Reducible Alkyd Enamel	○																																										
	V220 Rapid Dry Alkyd Enamel	○																																										
	V225 High Solids Rapid Dry Enamel	○																																										
	V230 Quick Dry Alkyd Enamel Gloss	○																																										
	V231 Quick Dry Alkyd Enamel Semi-Gloss	○																																										
V260 Electrostatic Enamel Semi-Gloss	○																																											
WB Acrylics	V300 Quick Dry Acrylic Spray DTM Gloss	○																																										
	V330 Acrylic DTM Enamel Gloss	○																																										
	V331 Acrylic DTM Enamel Semi-Gloss	○																																										
	V341 PreCatalyzed Waterborne Epoxy Semi-Gloss	○																																										
	V342 PreCatalyzed Waterborne Epoxy Eggshell	○																																										
2-Component Epoxies	V157 Coal Tar Epoxy	○																																										
	V160 Epoxy Mastic Coating	○																																										
	V400 Polyamide Epoxy Coating	○																																										
	V410 Fast Dry Polyamide Epoxy	○																																										
	V430 100% Solids Epoxy	○																																										
	V440 Amine Adduct Epoxy	○																																										
	V450 Acrylic Epoxy	○																																										
2-Component Urethanes	V500 Aliphatic Acrylic Urethane Gloss	○																																										
	V510 Aliphatic Acrylic Urethane Semi-Gloss	○																																										
	V515 Aliphatic Urethane Gloss	○																																										
	V520 Polyester Urethane Gloss	○																																										

NOTE: all coatings must be fully cured to meet these exposures
NOTE: this chart covers finish coats only. use primers recommended on individual finish coat technical data sheet
NOTE: proper surface preparation is critical to obtain resistance in all cases

Benjamin Moore & Co., Limited makes no guarantee as to the suitability of any product listed on this chart in the presence of any chemical reagent. All tests for resistance were completed under laboratory conditions. Temperature, humidity and other factors influence the rate at which certain chemicals react with coatings. For best results, test each coating in actual field conditions for suitability.

Fading and chalking may occur on certain product types, however chemical resistance is generally not compromised.

